

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

Claim 1 (Original): A catalyst composition comprising at least two metal components selected from Groups 8 to 10 of the Periodic Table of Elements and at least one metal component selected from Group 13 of the Periodic Table of Elements.

Claim 2 (Original): The catalyst composition of claim 1 wherein one of said at least two metal components selected from Groups 8 to 10 of the Periodic Table of Elements is rhodium.

Claim 3 (Original): The catalyst composition of claim 2 wherein another of said at least two metal components is selected from iron, ruthenium and cobalt.

Claim 4 (Original): The catalyst composition of claim 1 wherein said at least one metal component selected from Group 13 of the Periodic Table of Elements is indium.

Claim 5 (Original): The catalyst composition of claim 1 and further including a binder and/or support.

Claim 6 (Original): A catalyst composition comprising:

- (a) a first component comprising rhodium;
- (b) a second component comprising at least one metal selected from Group 13 of the Periodic Table of Elements; and
- (c) a third component comprising at least one metal different from said first and second components and selected from Groups 1 to 15 of the Periodic Table of Elements.

Claim 7 (Original): The catalyst composition of claim 6 and further including a support.

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

Claim 8 (Original): The catalyst composition of claim 7 and comprising from about 0.01 wt% to about 10 wt% of the first component, based on the rhodium metal present by weight of the total weight of the catalyst including the support.

Claim 9 (Original): The catalyst composition of claim 7 and comprising from about 0.04 wt% to about 5 wt% of the first component, based on the rhodium metal present by weight of the total weight of the catalyst including the support.

Claim 10 (Original): The catalyst composition of claim 7 and comprising from about 0.01 wt% to about 30 wt% of the second component, based on the amount of said Group 13 metal present by weight of the total weight of the catalyst including the support.

Claim 11 (Original): The catalyst composition of claim 7 and comprising from about 0.04 wt% to about 20 wt% of the second component, based on the amount of said Group 13 metal present by weight of the total weight of the catalyst including the support.

Claim 12 (Original): The catalyst composition of claim 7 wherein said second component comprises indium.

Claim 13 (Original): The catalyst composition of claim 12 and comprising from about 0.01 wt% to about 20 wt% of the second component, based on the amount of indium metal present by weight of the total weight of the catalyst including the support.

Claim 14 (Original): The catalyst composition of claim 11 and comprising from about 0.04 wt% to about 10 wt% of the second component, based on the amount of indium metal present by weight of the total weight of the catalyst including the support.

Claim 15 (Original): The catalyst composition of claim 7 and comprising from about 0.01 wt% to about 50 wt% of the third component, based on the amount of metal of said third component

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

present by weight of the total weight of the catalyst including the support.

Claim 16 (Original): The catalyst composition of claim 7 and comprising from about 0.05 wt% to about 30 wt% of the third component, based on the amount of metal of said third component present by weight of the total weight of the catalyst including the support.

Claim 17 (Original): The catalyst composition of claim 6 wherein said third component comprises at least one metal selected from Groups 8 to 10 of the Periodic Table of Elements.

Claim 18 (Original): The catalyst composition of claim 6 wherein said third component is selected from iron, ruthenium and cobalt.

Claim 19 (Original): The catalyst composition of claim 7 wherein the third component is iron and the catalyst composition comprises from about 0.05 wt% to about 30 wt% of the third component, based on the amount of iron metal present by weight of the total weight of the catalyst including the support.

Claim 20 (Original): The catalyst composition of claim 7 wherein the third component is iron and the catalyst composition comprises from about 0.1 wt% to about 20 wt% of the third component, based on the amount of iron metal present by weight of the total weight of the catalyst including the support.

Claim 21 (Original): The catalyst composition of claim 7 wherein the third component is cobalt and the catalyst composition comprises from about 0.05 wt% to about 30 wt% of the third component, based on the amount of cobalt metal present by weight of the total weight of the catalyst including the support.

Claim 22 (Original): The catalyst composition of claim 7 wherein the third component is cobalt and the catalyst composition comprises from about 0.1 wt% to about 25 wt% of the third

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

component, based on the amount of cobalt metal present by weight of the total weight of the catalyst including the support.

Claim 23 (Original): The catalyst composition of claim 7 wherein the third component is ruthenium and the catalyst composition comprises from about 0.05 wt% to about 10 wt% of the third component, based on the amount of ruthenium metal present by weight of the total weight of the catalyst including the support.

Claim 24 (Original): The catalyst composition of claim 7 wherein the third component is ruthenium and the catalyst composition comprises from about 0.1 wt% to about 5 wt% of the third component, based on the amount of ruthenium metal present by weight of the total weight of the catalyst including the support.

Claim 25 (Original): A catalyst composition comprising:

- (a) a first component comprising rhodium;
- (b) a second component comprising indium; and
- (c) a third component selected from one or more of iron, ruthenium and cobalt.

Claim 26 (Original): The catalyst composition of claim 25 and further including a support.

Claim 27 (Original): The catalyst composition of claim 26 and comprising from about 0.01 wt% to about 10 wt% of the first component, based on the rhodium metal present by weight of the total weight of the catalyst including the support.

Claim 28 (Original): The catalyst composition of claim 26 and comprising from about 0.04 wt% to about 5 wt% of the first component, based on the rhodium metal present by weight of the total weight of the catalyst including the support.

Claim 29 (Original): The catalyst composition of claim 26 and comprising from about 0.01 wt%

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

to about 20 wt% of the second component, based on the indium metal present by weight of the total weight of the catalyst including the support.

Claim 30 (Original): The catalyst composition of claim 26 and comprising from about 0.04 wt% to about 10 wt% of the second component, based on the indium metal present by weight of the total weight of the catalyst including the support.

Claim 31 (Original): The catalyst composition of claim 26 wherein the third component is iron and the catalyst composition comprises from about 0.05 wt% to about 30 wt% of the third component, based on the amount of iron metal present by weight of the total weight of the catalyst including the support.

Claim 32 (Original): The catalyst composition of claim 26 wherein the third component is iron and the catalyst composition comprises from about 0.1 wt% to about 20 wt% of the third component, based on the amount of iron metal present by weight of the total weight of the catalyst including the support.

Claim 33 (Original): The catalyst composition of claim 26 wherein the third component is cobalt and the catalyst composition comprises from about 0.05 wt% to about 30 wt% of the third component, based on the amount of cobalt metal present by weight of the total weight of the catalyst including the support.

Claim 34 (Original): The catalyst composition of claim 26 wherein the third component is cobalt and the catalyst composition comprises from about 0.1 wt% to about 25 wt% of the third component, based on the amount of cobalt metal present by weight of the total weight of the catalyst including the support.

Claim 35 (Original): The catalyst composition of claim 26 wherein the third component is ruthenium and the catalyst composition comprises from about 0.05 wt% to about 10 wt% of the

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

third component, based on the amount of ruthenium metal present by weight of the total weight of the catalyst including the support.

Claim 36 (Original): The catalyst composition of claim 26 wherein the third component is ruthenium and the catalyst composition comprises from about 0.1 wt% to about 5 wt% of the third component, based on the amount of ruthenium metal present by weight of the total weight of the catalyst including the support.

Claim 37 (Original): The catalyst composition of claim 25 wherein the molar ratio of rhodium to indium is from about 0.1 to about 1.2.

Claim 38 (Original): The catalyst composition of claim 25 wherein the molar ratio of rhodium to indium is from about 0.3 to about 0.9.

Claim 39 (Original): The catalyst composition of claim 25 wherein the molar ratio of rhodium to the metal of the third component is from about 0.001 to about 0.6.

Claim 40 (Original): The catalyst composition of claim 25 wherein the molar ratio of rhodium to the metal of the third component is from about 0.002 to about 0.3.

Claim 41 (Original): The catalyst composition of claim 26 wherein the support is selected from zirconia, alumina and ceria-alumina.

Claim 42 (Original): A method of making a catalyst composition, the method comprising:

- (a) applying a rhodium compound to a support;
- (b) applying a compound of a metal selected from Group 13 of the Periodic Table of Elements to the support; and
- (c) applying a compound of a further metal different from rhodium and from said Group 13 metal and selected from Groups 1 to 15 of the Periodic Table of Elements to the support.

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

Claim 43 (Original): The method of claim 42 wherein said further metal compound is applied to the support before either the rhodium compound or the Group 13 metal compound.

Claim 44 (Original): The method of claim 42 wherein the rhodium compound and the Group 13 metal compound are applied to the support concurrently.

Claim 45 (Original): The method of claim 42 wherein the Group 13 metal compound is applied to the support before the rhodium compound.

Claim 46 (Original): The method of claim 42 wherein the rhodium compound is rhodium nitrate.

Claim 47 (Original): The method of claim 42 wherein the Group 13 metal compound is an indium compound.

Claim 48 (Original): The method of claim 47 wherein the indium compound is indium nitrate or indium formate.

Claim 49 (Original): The method of claim 42 wherein the further metal compound is selected from iron, cobalt and ruthenium compounds.

Claim 50 (Original): The method of claim 42 wherein at least one of the compounds is applied to the support by impregnating the support with a solution of the compound.

Claim 51 (Original): The method of claim 42 wherein at least one of the compounds is applied to the support by precipitating the compound from a solution containing ions of the associated metal.

Claim 52 (Original): The method of claim 42 and, after (a) and/or (b) and/or (c), calcining the support at a temperature of about 100°C to about 600°C.

USSN: 10/720,558
Atty. Docket No.: 2003B124
Amdt. dated March 30, 2005
Reply to Office Action of November 30, 2004

Claim 53 (Original): The method of claim 42 and, after (a), (b) and (c), treating the calcined support in a reducing atmosphere at a temperature in excess of 200°C.

Claim 54 (Withdrawn): A process for selectively removing alkynes or diolefins from a feedstock also containing olefins, the process comprising contacting the feedstock with hydrogen in the presence of a catalyst composition made by the method of claim 42.

Claim 55 (Withdrawn): A process for selectively removing alkynes or diolefins from a feedstock also containing olefins, the process comprising contacting the feedstock with hydrogen in the presence of a catalyst composition comprising at least two different metal components selected from Groups 8 to 10 of the Periodic Table of Elements and at least one metal component selected from Group 13 of the Periodic Table of Elements.

Claim 56 (Withdrawn): The process of claim 55 wherein the alkynes or diolefins have 2 to 4 carbon atoms and the feedstock also contains C₂ to C₄ olefins.

Claim 57 (Withdrawn): A process for selectively removing C₂ to C₄ alkynes or diolefins from a feedstock also containing C₂ to C₄ olefins, the process comprising contacting the feedstock with hydrogen in the presence of a catalyst composition comprising at least two different metal components selected from Groups 8 to 10 of the Periodic Table of Elements and at least one metal component selected from Group 13 of the Periodic Table of Elements, and the process producing an olefin-enriched product stream containing less than 20 weight % oligomerized alkyne and diolefin compounds, based on the weight of said oligomerized alkyne and diolefin compounds in said product stream by the weight of said feedstock.

Claim 58 (Withdrawn): The process of claim 57 and producing an olefin-enriched product stream containing less than 10 weight % oligomerized alkyne and diolefin compounds, based on the weight of said oligomerized alkyne and diolefin compounds in said product stream by the weight of said feedstock.

USSN: 10/720,558

Atty. Docket No.: 2003B124

Amdt. dated March 30, 2005

Reply to Office Action of November 30, 2004

Claim 59 (Withdrawn): A process for selectively removing alkynes or diolefins from a feedstock also containing olefins, the process comprising contacting the feedstock with hydrogen in the presence of a catalyst composition comprising

- (a) a first component comprising rhodium;
- (b) a second component comprising indium; and
- (c) a third component selected from one or more of iron, ruthenium and cobalt.

Claim 60 (Withdrawn): The process of claim 59 wherein the alkynes or diolefins have 2 to 4 carbon atoms and the feedstock also contains C₂ to C₄ olefins.

Claim 61 (Withdrawn): The process of claim 59 wherein said contacting is conducted at a temperature of from about 20°C to about 150°C, a pressure of from about 690 kPa to 4100 kPa, and a molar ratio of hydrogen to alkynes and diolefins of from about 1 to about 1000.

Claim 62 (Withdrawn): The process of claim 59 wherein said contacting is conducted at a temperature of from about 30°C to about 100°C, a pressure of from about 1400 kPa to 3400 kPa, and a molar ratio of hydrogen to alkynes and diolefins of from about 1.1 to about 800.